

Product:

2300 Tripolymer



Dry Adhesion (lbf/failure mode)	Clear	Colors
Aluminum	17.18/100a	17.69/100a
Brick	15.07/100a	14.69/100a
Concrete	20.72/100a	25.43/100a
Copper	28.73/10c	
Galvanized Steel	25.04/100a	22.83/100a
Glass	48.64/100c	Wire Broke
Kynar	25.28/100a	Wire Broke
Luan (Wood)	17.07/100a	21.20/100a
Shingle	3.59/100a	7.48/100a
Steel	31.26/100a	29.37/100a
Tile	Wire Broke	Wire Broke
Vinyl	18.97/100a	20.72/100a
Tensile at Peak (psi)	500	480
Elongation at Break (%)	1062	1194
Type "A" Hardness	20	25
Tack Free Time (ASTM method)	45 mins	30 mins
Cure Rate by Weight Loss (Internal)	4 days	4 days
Product test date	6/13	6/13

Geocel Products Group
A Business Unit of the Sherwin-Williams Company
Cleveland, OH 44115

Questions?

Call Customer Service at 800-348-7615

Title:	TP Product Spec Template	Location:	W:\BMS Site Forms
Document Code:	EK - 2-57	Revision Number:	0
Issue Date:	5/20/2014	Page:	1 of 1
Author:	Plant Quality Manager	Approver:	Plant Quality Manager